

Product Data Sheet

ProStripe Plus[™]

Waterborne Acrylic Traffic Paint

Description: Excellent fast-dry traffic paint with a 100% acrylic binder in conjunction with

high quality powdered pigments, binders, and liquid drier to produce a good cost/performance balanced paint that possesses the environmental advantages of a waterborne system. An excellent environmentally friendly, lead-free, low VOC paint that is especially designed for the airless walk-behind stripers. Prostripe Plus is an excellent paint for application on asphaltic parking lots and

low volume roadways.

Directions: Do not mix with other paints. Do not tint. Do not apply at temperatures less

than 50°F(10°C) humidity over 85%, or if rain is expected within one hour. Strain into striping tank through a 16 mesh screen to prevent clogging of equipment. After use, equipment should be cleaned promptly. If glass bead application is required for retroreflectivity, manufacturer's instructions should be followed.

Surface Preparation: Surface should be dry, clean and free of grease, dust and other foreign matter.

May be used on freshly sealed asphalt surfaces, coal tar surfaces, and concrete

and as a primer for alkyd-based traffic paints.

Material Preparation: Mix thoroughly. Ready to use for most applications. If thinning is necessary do

not exceed 12oz. of water per five gallons of paint.

Precautions: All surfaces exposed to waterborne paints must be stainless steel, coated metal

or plastic, due to a chemical reaction.

Specifications: Exceeds Federal spec. TTP-1952-E (Type I, II).

Colors: White, Yellow, Black, Blue, Red

This information is to assist customers in determining if this product is suitable for the proposed application, and to satisfy themselves as to the suitability of the contents. Nothing herein shall constitute a warranty, express or implied, including any warranty of merchantability or fitness, nor is protection from any law or patent implied.

Copyright© 2019 GemSeal Pavement Products.





Product Data Sheet

ProStripe Plus[™]

Waterborne Acrylic Traffic Paint

Specifications:	Dry time:	No Tracking (open to traffic) 190 seconds at	(ASTM 711)
-----------------	-----------	--	------------

//		7	7	°f	
----	--	---	---	----	--

	Dry-Through (early washout) 120 minutes at 73°f	(ASTM D1640)
Lead Content:	<0.06%	(ASTM D3335)
Viscosity:	80-90 Krebs Units	(ASTM D563)
Grind:	5	(ASTM 1210)
Pigment Percent:	60% – 62%	(ASTM D3723)
Dry Opacity Ratio:	.94 – 100	(ASTM 2805)
Abrasion Resistance:	Passes	(ASTM D968)
Reflectance:	85% White	(ASTM E1347)
Flexibility:	Passes	(ASTM D522)
Bleeding:	.95 Min	(ASTM D969)
Volatile Organic Content VOC:	75 - 85 grams/ltr	(ASTM D2369)
Non-Volatile:	42% Min	(ASTM D2697)
Heat-Shear Consistency:	68-105 KUs	
pH Value:	10. +	
Weight Per Gallon:	14.0 +25lbs	
Total Solids:	75% Min	

Coverage: One gallon will provide a 4 inch (10.16cm) wide stripe approximately 370 linear feet (106.68M) at

a wet film thickness of 13 mils (measured without glass beads).

Packaging: Available in 250 gallon totes, 50 gallon (208.18 liter) drums or 5 gallon (18.93 liter) pails.

Application Clean, Dry Surface

Perameters: Ambient and surface temperature between 50f and 100f

Relative Humidity of less than 85%

Airless Spray application at 13-15 mils wet thickness

Asphalt or concrete surfaces

For Retroreflectivity apply glass beads: 9 lbs/Gal. (1.08kg/ Liter)

This information is to assist customers in determining if this product is suitable for the proposed application, and to satisfy themselves as to the suitability of the contents. Nothing herein shall constitute a warranty, express or implied, including any warranty of merchantability or fitness, nor is protection from any law or patent implied.

Copyright© 2019 GemSeal Pavement Products.

