Technical Data



CRACK-FLEX

PRO-S

DESCRIPTION: GemSeal CRACK FLEX PRO-S is a hot applied joint and crack sealing compound formulated with selected

asphaltic resins, synthetic polymeric rubber, plasticizers, stabilizers, and a blend of organic reinforcing fillers. This construction grade material is a one-part sealer that provides excellent results under extremely varying conditions. GemSeal CRACK FLEX PRO-S is perfect for use in applications that are susceptible to tracking and picking up, such as pedestrian foot traffic and vehicle power steering in high temperature conditions.

FEATURES:

- Construction grade joint and crack sealing compound for concrete and asphaltic pavements.
- Economical and effective preventative maintenance treatment.
- Prolongs the pavement service life.
- Seals cracks and joints from water penetration.
- Extreme high temperature conditions
- Fast melt, easy pour, fast set
- Passes multiple freeze and thaw cycles

USE:

- Parking Lots
- Plaza Decks
- Driveways

APPLICATIONS

GemSeal* CRACK-FLEX PRO-S is recommended for sealing of joints and cracks in concrete and asphaltic pavements and

parking lots. It is designed for use in sealing expansion and contraction joints as well as random cracks.

TYPICAL PROPERTIES:

Recommended P	370°F - 390°F	
Maximum Heatir	400°F	
Recommended E	6 Hours	
Penetration (150g	90 max.	
Flow at 140°F	3 mm max.	
Softening Point 7	176°F min.	
Bond - 50% Ext	Passes 3 cycles	
Asphalt Compati	Compatible	
		1
Width	Depth	Pounds/100 lineal feet
	Depth 3/8"	Pounds/100
Width	1	Pounds/100 lineal feet
Width 3/8"	3/8"	Pounds/100 lineal feet 6.9
Width 3/8" 3/8"	3/8" 1/2"	Pounds/100 lineal feet 6.9 9.3
Width 3/8" 3/8" 1/2"	3/8" 1/2" 1/2"	Pounds/100 lineal feet 6.9 9.3 12.3

SURFACE PREPARATION:

To facilitate proper adhesion, the joint or crack should be dry and clear of any dirt, dust or other contaminates. Substrate and ambient temperatures must be 40°F or above. Proper sizing of the joint will cause the maximum extension/compression to not

the joint will cause the maximum extension/compression to not exceed 50% of the width. Joints or random cracks of 1/4" or less are difficult to properly clean prior to applying the sealant.

EQUIPMENT:

Use an agitated oil-jacketed or direct fired unit with agitation that has separate temperature gauges for both the sealant and the heat transfer fluid. Take the 30 lb. plastic bag of sealant and load into the kettle one at a time. Melt only enough material for the day's activities. Once melted, additional material can be added as needed. Material can be safely reheated within the sealants service life.

NOTE: Prolonged heating of the sealant above the maximum safe heating temperature may cause it to gel in the kettle.

SERVICE LIFE:

The service life (pot-life) at application temperatures is approximately 12 hours. Adding fresh material to the melter as sealant is being used will extend the service life. Material that has been overheated can thicken and gel in the melter.

Any material that has exceeded the service life should be removed from the melter and discarded.

COVERAGE RATE:

PACKAGING:

is packaged in a 30 lb. polybag inside a high strength corrugated box. each pallet contains 75 boxes or 2,250 pounds

This product is heated to high temperatures during application. Skin contact with heated material can cause severe burns. Wear protective clothing, safety glasses and gloves always while using this product.

MANUFACTURING & CUSTOMER SERVICE:

Call (866) 264-8273 to find the nearest GemSeal location to purchase Crack-Flex Pro-S GemSeal Pavement Products Corporate Headquarters:

3700 Arco Corporate Drive, Suite 425 Charlotte, NC 28273

performance standards listed in the technical data sheet for the product at the time of sale, if used as directed and within the stated shelf life. This Limited Warranty applies only if the product is stored, used, and applied over a properly prepared substrate in strict accordance with applicable specifications and instructions issued by GemSeal Pavement Products. The Limited Warranty will not apply if the product is altered, modified, or misused after it has left the control of GemSeal Pavement Products. GemSeal Pavement Products will not be responsible for defects caused by factors beyond its control, including but not limited to workmanship, application equipment, weather, acts of God, structural failure, condition or movement of substrate, improper additives, poor drainage, ponded water, improper maintenance, damage from snow removal equipment, and normal wear and tear. GemSeal Pavement Products does not warrant that the product or any method of use or application would be suitable for any particular site conditions. All warranty claims must be submitted in writing, with proof of purchase, to the following address: 3700 Arco Corporate Drive, Suite 425, Charlotte, NC 28273. Unused portions of product must be returned upon request. Replacement of defective product or, at GemSeal Pavement Products' option, refund of the purchase price of defective product shall be the buyer's sole remedy under this Limited Warranty. In no event shall GemSeal Pavement Products be liable for any damages in excess of the purchase price of the defective product. This Limited Warranty does not cover labor costs for product application, replacement, or repair. GEMSEAL PAVEMENT PRODUCTS SHALL IN NO EVENT BE LIABLE FOR CONSEQUENTIAL, INCIDENTAL, OR SPECIAL DAMAGES, INCLUDING BUT NOT LIMITED TO DAMAGES FOR LOST SALES OR PROFITS, BUSINESS INTERRUPTION, DELAYS, PHYSICAL DAMAGE TO OTHER MATERIALS OR PROPERTY, OR LOSS OF USE OF PROPERTY. THIS LIMITED WARRANTY IS PROVIDED IN LIEU OF ALL OTHER WARRANTIES, EXPRESS OR IMPLIED. GEMSEAL PAVEMENT PRODUCTS EXPRESSLY DISCLAIMS ANY OTHER WARRANTIES, INCLUDING IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. No modification or extension of this Limited Warranty shall be valid unless given in writing and signed by an authorized officer of GemSeal Pavement Products. Sales personnel and product distributors are not authorized to modify or extend this Limited Warranty.

GemSeal Pavement Products warrants that for a period of one (1) year from date of purchase this product shall be free from manufacturing defects and shall meet or exceed

